

## LASF35 022291.541

|                 |               |                              |
|-----------------|---------------|------------------------------|
| $n_d = 2.02204$ | $v_d = 29.06$ | $n_F - n_C = 0.035170$       |
| $n_e = 2.03035$ | $v_e = 28.84$ | $n_{F'} - n_{C'} = 0.035721$ |

| Refractive Indices |                |         |
|--------------------|----------------|---------|
|                    | $\lambda$ [nm] |         |
| $n_{2325.4}$       | 2325.4         | 1.95946 |
| $n_{1970.1}$       | 1970.1         | 1.96639 |
| $n_{1529.6}$       | 1529.6         | 1.97472 |
| $n_{1060.0}$       | 1060.0         | 1.98624 |
| $n_t$              | 1014.0         | 1.98786 |
| $n_s$              | 852.1          | 1.99531 |
| $n_r$              | 706.5          | 2.00628 |
| $n_C$              | 656.3          | 2.01185 |
| $n_{C'}$           | 643.8          | 2.01343 |
| $n_{632.8}$        | 632.8          | 2.01493 |
| $n_D$              | 589.3          | 2.02173 |
| $n_d$              | 587.6          | 2.02204 |
| $n_e$              | 546.1          | 2.03035 |
| $n_F$              | 486.1          | 2.04702 |
| $n_{F'}$           | 480.0          | 2.04916 |
| $n_g$              | 435.8          | 2.06805 |
| $n_h$              | 404.7          | 2.08663 |
| $n_i$              | 365.0          |         |
| $n_{334.1}$        | 334.1          |         |
| $n_{312.6}$        | 312.6          |         |
| $n_{296.7}$        | 296.7          |         |
| $n_{280.4}$        | 280.4          |         |
| $n_{248.3}$        | 248.3          |         |

| Internal Transmittance $\tau_i$ |                 |                 |
|---------------------------------|-----------------|-----------------|
| $\lambda$ [nm]                  | $\tau_i$ (10mm) | $\tau_i$ (25mm) |
| 2500                            | 0.787           | 0.550           |
| 2325                            | 0.877           | 0.720           |
| 1970                            | 0.973           | 0.934           |
| 1530                            | 0.995           | 0.987           |
| 1060                            | 0.998           | 0.994           |
| 700                             | 0.992           | 0.981           |
| 660                             | 0.990           | 0.974           |
| 620                             | 0.987           | 0.969           |
| 580                             | 0.985           | 0.962           |
| 546                             | 0.977           | 0.943           |
| 500                             | 0.948           | 0.874           |
| 460                             | 0.903           | 0.774           |
| 436                             | 0.852           | 0.670           |
| 420                             | 0.787           | 0.550           |
| 405                             | 0.686           | 0.390           |
| 400                             | 0.634           | 0.320           |
| 390                             | 0.504           | 0.180           |
| 380                             | 0.302           | 0.050           |
| 370                             | 0.100           |                 |
| 365                             | 0.030           |                 |
| 350                             |                 |                 |
| 334                             |                 |                 |
| 320                             |                 |                 |
| 310                             |                 |                 |
| 300                             |                 |                 |
| 290                             |                 |                 |
| 280                             |                 |                 |
| 270                             |                 |                 |
| 260                             |                 |                 |
| 250                             |                 |                 |

| Relative Partial Dispersion |        |
|-----------------------------|--------|
| $P_{s,t}$                   | 0.2118 |
| $P_{C,s}$                   | 0.4701 |
| $P_{d,C}$                   | 0.2899 |
| $P_{e,d}$                   | 0.2364 |
| $P_{g,F}$                   | 0.5982 |
| $P_{i,h}$                   |        |
| $P'_{s,t}$                  | 0.2086 |
| $P'_{C',s}$                 | 0.5073 |
| $P'_{d,C'}$                 | 0.2409 |
| $P'_{e,d}$                  | 0.2327 |
| $P'_{g,F'}$                 | 0.5291 |
| $P'_{i,h}$                  |        |

### Deviation of Relative Partial Dispersions $\Delta P$ from the "Normal Line"

|                  |         |
|------------------|---------|
| $\Delta P_{C,t}$ | -0.0009 |
| $\Delta P_{C,s}$ | -0.0006 |
| $\Delta P_{F,e}$ | 0.0006  |
| $\Delta P_{g,F}$ | 0.0033  |
| $\Delta P_{i,g}$ |         |

| Constants of Dispersion Formula |              |
|---------------------------------|--------------|
| $B_1$                           | 2.45505861   |
| $B_2$                           | 0.453006077  |
| $B_3$                           | 2.3851308    |
| $C_1$                           | 0.0135670404 |
| $C_2$                           | 0.054580302  |
| $C_3$                           | 167.904715   |

| Constants of Dispersion $dn/dT$ |                        |
|---------------------------------|------------------------|
| $D_0$                           | $1.43 \cdot 10^{-7}$   |
| $D_1$                           | $8.71 \cdot 10^{-9}$   |
| $D_2$                           | $-2.71 \cdot 10^{-11}$ |
| $E_0$                           | $1.02 \cdot 10^{-6}$   |
| $E_1$                           | $1.50 \cdot 10^{-9}$   |
| $\lambda_{TK} [\mu m]$          | 0.263                  |

| Color Code                     |        |
|--------------------------------|--------|
| $\lambda_{80}/\lambda_5$       | 45/37* |
| (*= $\lambda_{70}/\lambda_5$ ) |        |

| Remarks |
|---------|
|         |

| Other Properties                        |       |
|---|-------|
| $\alpha_{-30/+70^\circ C} [10^{-6}/K]$  | 7.4   |
| $\alpha_{+20/+300^\circ C} [10^{-6}/K]$ | 8.5   |
| $T_g [^\circ C]$                        | 774   |
| $T_{10}^{13.0} [^\circ C]$              | 0     |
| $T_{10}^{7.6} [^\circ C]$               | 0     |
| $c_p [J/(g \cdot K)]$                   | 0.445 |
| $\lambda [W/(m \cdot K)]$               | 0.920 |
| $\rho [g/cm^3]$                         | 5.41  |
| $E [10^3 N/mm^2]$                       | 132   |
| $\mu$                                   | 0.303 |
| $K [10^{-6} mm^2/N]$                    | 0.73  |
| $HK_{0.1/20}$                           | 810   |
| $HG$                                    | 1     |
| $CR$                                    | 1     |
| $FR$                                    | 0     |
| $SR$                                    | 1.3   |
| $AR$                                    | 1     |
| $PR$                                    | 1.3   |

| Temperature Coefficients of Refractive Index |                                       |     |     |                                       |     |     |
|--|---------------------------------------|-----|-----|---------------------------------------|-----|-----|
| [ $^\circ C$ ]                               | $\Delta n_{rel}/\Delta T [10^{-6}/K]$ |     |     | $\Delta n_{abs}/\Delta T [10^{-6}/K]$ |     |     |
|  | 1060.0                                | e   | g   | 1060.0                                | e   | g   |
| -40/ -20                                     | 2.6                                   | 5.0 | 7.8 | -0.1                                  | 2.2 | 5.0 |
| +20/ +40                                     | 2.7                                   | 5.5 | 9.0 | 1.0                                   | 3.8 | 7.1 |
| +60/ +80                                     | 2.8                                   | 5.9 | 9.7 | 1.4                                   | 4.5 | 8.3 |