

N-ZK7 508612.249

$n_d = 1.50847$	$v_d = 61.19$	$n_F - n_C = 0.008310$
$n_e = 1.51045$	$v_e = 60.98$	$n_{F'} - n_{C'} = 0.008370$

Refractive Indices		
	λ [nm]	
$n_{2325.4}$	2325.4	1.48062
$n_{1970.1}$	1970.1	1.48637
$n_{1529.6}$	1529.6	1.49233
$n_{1060.0}$	1060.0	1.49813
n_t	1014.0	1.49876
n_s	852.1	1.50129
n_r	706.5	1.50445
n_C	656.3	1.50592
$n_{C'}$	643.8	1.50633
$n_{632.8}$	632.8	1.50671
n_D	589.3	1.50840
n_d	587.6	1.50847
n_e	546.1	1.51045
n_F	486.1	1.51423
$n_{F'}$	480.0	1.51470
n_g	435.8	1.51869
n_h	404.7	1.52238
n_i	365.0	1.52865
$n_{334.1}$	334.1	1.53538
$n_{312.6}$	312.6	1.54155
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Internal Transmittance τ_i		
λ [nm]	τ_i (10mm)	τ_i (25mm)
2500	0.657	0.350
2325	0.847	0.660
1970	0.971	0.930
1530	0.990	0.976
1060	0.998	0.994
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.995	0.988
436	0.994	0.984
420	0.992	0.981
405	0.991	0.977
400	0.990	0.975
390	0.987	0.969
380	0.982	0.956
370	0.976	0.940
365	0.971	0.930
350	0.941	0.860
334	0.852	0.670
320	0.686	0.390
310	0.492	0.170
300	0.221	0.030
290	0.032	
280		
270		
260		
250		

Relative Partial Dispersion	
$P_{s,t}$	0.3049
$P_{C,s}$	0.5570
$P_{d,C}$	0.3069
$P_{e,d}$	0.2386
$P_{g,F}$	0.5370
$P_{i,h}$	0.7543
$P'_{s,t}$	0.3027
$P'_{C',s}$	0.6017
$P'_{d,C'}$	0.2560
$P'_{e,d}$	0.2369
$P'_{g,F'}$	0.4771
$P'_{i,h}$	0.7488

Deviation of Relative Partial Dispersions ΔP from the "Normal Line"

$\Delta P_{C,t}$	0.0267
$\Delta P_{C,s}$	0.0115
$\Delta P_{F,e}$	-0.0017
$\Delta P_{g,F}$	-0.0039
$\Delta P_{i,g}$	-0.0129

Constants of Dispersion Formula	
B_1	1.07715032
B_2	0.168079109
B_3	0.851889892
C_1	0.00676601657
C_2	0.0230642817
C_3	89.0498778

Constants of Dispersion dn/dT	
D_0	$1.15 \cdot 10^{-5}$
D_1	$1.73 \cdot 10^{-8}$
D_2	$-8.06 \cdot 10^{-11}$
E_0	$4.32 \cdot 10^{-7}$
E_1	$7.05 \cdot 10^{-10}$
$\lambda_{TK} [\mu m]$	0.179

Color Code	
λ_{80}/λ_5	34/29
(* = λ_{70}/λ_5)	

Remarks	

Other Properties	
$\alpha_{-30/+70^\circ C} [10^{-6}/K]$	4.5
$\alpha_{+20/+300^\circ C} [10^{-6}/K]$	5.2
$T_g [^\circ C]$	539
$T_{10}^{13.0} [^\circ C]$	0
$T_{10}^{7.6} [^\circ C]$	721
$c_p [J/(g \cdot K)]$	0.770
$\lambda [W/(m \cdot K)]$	1.042
$\rho [g/cm^3]$	2.49
$E [10^3 N/mm^2]$	70
μ	0.214
$K [10^{-6} mm^2/N]$	3.63
$HK_{0.1/20}$	530
HG	4
CR	1
FR	0
SR	2
AR	1.2
PR	2.2

Temperature Coefficients of Refractive Index						
[$^\circ C$]	$\Delta n_{rel}/\Delta T [10^{-6}/K]$			$\Delta n_{abs}/\Delta T [10^{-6}/K]$		
	1060.0	e	g	1060.0	e	g
-40/ -20	5.9	6.5	7.0	3.9	4.5	4.9
+20/ +40	6.4	7.0	7.6	5.1	5.7	6.3
+60/ +80	6.4	7.2	7.8	5.4	6.2	6.8