

D 263® T Thin Glass

D 263® T eco thin glass is a clear borosilicate glass that has a high chemical resistance and is produced by a SCHOTT specific down-draw method. It is available in a variety of thicknesses ranging from 0.03 mm to 1.1 mm.

D 263® T eco borosilicate glass is available in standard stock size sheets or can be custom cut into round or square shapes.

D 263® T eco thin glass is used as substrate glass for coatings or as replacement for plastic for applications in the automotive and electronics industries.

D 263® T eco is manufactured with eco-friendly refining agents.




Applications



Resistive touch panel for built-in car navigation

- Stable against sunlight and heat
- Not permeable to humidity
- Flexibility is similar to that of plastic
- Easy to cut by laser or scribe and break method



Optocaps in laser diodes

- High luminous transmittance
- Easy to process
- Coefficient of thermal expansion match with metals for hermetic sealings



Substrate glass for IR cut-off filter for camera modules in mobile phones

- High luminous transmittance
- Easy to dice by diamond saw
- Coatings adhere well due to excellent surface quality
- Smooth surface for coatings without previous polishing
- Range of thin thicknesses enables easy adaptation for future product miniaturization

Technical Data

Dimensions	440 mm x 360 mm, other size on request
Thicknesses	0.03 mm up to 1.1 mm
Luminous transmittance τ_{vD65} (d = 1.1 mm)	91.7 %
Coefficient of mean linear thermal expansion α (20 °C; 300 °C) (static measurement)	$7.2 \cdot 10^{-6} \text{ K}^{-1}$
Transformation temperature T_g	557 °C
Dielectric constant ϵ_r at 1MHz	6.7
Refractive index n_D	1.5230
Density ρ (annealed at 40 °C/h)	2.51 g/cm ³

For more information please contact:

Advanced Optics
SCHOTT AG
Hattenbergstrasse 10
55122 Mainz
Germany

Phone: +49 (0)6131/66-1812
Fax: +49 (0)3641/2888-9047
info.thinglass@schott.com
www.schott.com/advanced_optics

SCHOTT
glass made of ideas