

**SF57**  
**847238.551**

$n_d = 1.84666$	$v_d = 23.83$	$n_F - n_C = 0.035536$
$n_e = 1.85504$	$v_e = 23.64$	$n_{F'} - n_{C'} = 0.036166$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.79026
$n_{1970.1}$	1970.1	1.79539
$n_{1529.6}$	1529.6	1.80187
$n_{1060.0}$	1060.0	1.81185
$n_t$	1014.0	1.81335
$n_s$	852.1	1.82038
$n_r$	706.5	1.83102
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83808
$n_{632.8}$	632.8	1.83957
$n_D$	589.3	1.84636
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87204
$n_{F'}$	480.0	1.87425
$n_g$	435.8	1.89393
$n_h$	404.7	1.91366
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ (10mm)	$\tau_i$ (25mm)
2500	0.891	0.750
2325	0.910	0.790
1970	0.971	0.930
1530	0.996	0.991
1060	0.999	0.997
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.994
546	0.998	0.994
500	0.994	0.986
460	0.987	0.968
436	0.971	0.930
420	0.941	0.860
405	0.882	0.730
400	0.847	0.660
390	0.727	0.450
380	0.523	0.198
370	0.160	0.010
365	0.040	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

Relative Partial Dispersion	
$P_{s,t}$	0.1976
$P_{C,s}$	0.4539
$P_{d,C}$	0.2859
$P_{e,d}$	0.2356
$P_{g,F}$	0.6160
$P_{i,h}$	
$P'_{s,t}$	0.1942
$P'_{C',s}$	0.4895
$P'_{d,C'}$	0.2373
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

Deviation of Relative Partial Dispersions $\Delta P$ from the "Normal Line"	
$\Delta P_{C,t}$	-0.0065
$\Delta P_{C,s}$	-0.0046
$\Delta P_{F,e}$	0.0026
$\Delta P_{g,F}$	0.0123
$\Delta P_{i,g}$	

Constants of Dispersion Formula	
$B_1$	1.81651371
$B_2$	0.428893641
$B_3$	1.07186278
$C_1$	0.0143704198
$C_2$	0.0592801172
$C_3$	121.419942

Constants of Dispersion $dn/dT$	
$D_0$	$7.26 \cdot 10^{-6}$
$D_1$	$1.88 \cdot 10^{-8}$
$D_2$	$-5.14 \cdot 10^{-11}$
$E_0$	$1.96 \cdot 10^{-6}$
$E_1$	$1.79 \cdot 10^{-9}$
$\lambda_{TK} [\mu m]$	0.276

Color Code	
$\lambda_{80}/\lambda_5$	40/37*
(*= $\lambda_{70}/\lambda_5$ )	

**Remarks**  
lead containing glass type, suitable for precision molding

Other Properties	
$\alpha_{-30/+70^\circ C} [10^{-6}/K]$	8.3
$\alpha_{+20/+300^\circ C} [10^{-6}/K]$	9.2
$T_g [^\circ C]$	414
$T_{10}^{13.0} [^\circ C]$	391
$T_{10}^{7.6} [^\circ C]$	519
$c_p [J/(g \cdot K)]$	0.360
$\lambda [W/(m \cdot K)]$	0.620
$AT [^\circ C]$	449
$\rho [g/cm^3]$	5.51
$E [10^3 N/mm^2]$	54
$\mu$	0.248
$K [10^{-6} mm^2/N]$	0.02
$HK_{0.1/20}$	350
$HG$	1
<b>Abrasion Aa</b>	344
<b>CR</b>	2
<b>FR</b>	5
<b>SR</b>	52.3
<b>AR</b>	2.3
<b>PR</b>	4.3
<b>SR-J</b>	6
<b>WR-J</b>	1

Temperature Coefficients of Refractive Index						
[ $^\circ C$ ]	$\Delta n_{rel}/\Delta T [10^{-6}/K]$			$\Delta n_{abs}/\Delta T [10^{-6}/K]$		
	1060.0	e	g	1060.0	e	g
-40/ -20	6.6	11.1	16.7	4.2	8.6	14.1
+20/ +40	7.6	12.5	18.9	6.0	10.9	17.2
+60/ +80	8.0	13.4	20.1	6.8	12.1	18.8