

**K10**  
**501564.252**

$n_d = 1,50137$	$v_d = 56,41$	$n_F - n_C = 0,008888$
$n_e = 1,50349$	$v_e = 56,15$	$n_{F'} - n_{C'} = 0,008967$

Brechzahlen		
	$\lambda$ [nm]	
$n_{2325,4}$	2325,4	1,47507
$n_{1970,1}$	1970,1	1,48008
$n_{1529,6}$	1529,6	1,48536
$n_{1060,0}$	1060,0	1,49076
$n_t$	1014,0	1,49137
$n_s$	852,1	1,49389
$n_r$	706,5	1,49713
$n_C$	656,3	1,49867
$n_{C'}$	643,8	1,49910
$n_{632,8}$	632,8	1,49950
$n_D$	589,3	1,50129
$n_d$	587,6	1,50137
$n_e$	546,1	1,50349
$n_F$	486,1	1,50756
$n_{F'}$	480,0	1,50807
$n_g$	435,8	1,51243
$n_h$	404,7	1,51649
$n_i$	365,0	1,52350
$n_{334,1}$	334,1	1,53120
$n_{312,6}$	312,6	1,53844
$n_{296,7}$	296,7	
$n_{280,4}$	280,4	
$n_{248,3}$	248,3	

Reintransmissionsgrad $\tau_i$		
$\lambda$ [nm]	$\tau_i$ (10mm)	$\tau_i$ (25mm)
2500	0,770	0,520
2325	0,831	0,630
1970	0,937	0,850
1530	0,993	0,983
1060	0,998	0,996
700	0,999	0,997
660	0,998	0,994
620	0,997	0,993
580	0,997	0,993
546	0,997	0,992
500	0,996	0,991
460	0,996	0,990
436	0,995	0,988
420	0,995	0,988
405	0,995	0,987
400	0,994	0,986
390	0,993	0,982
380	0,989	0,973
370	0,986	0,966
365	0,983	0,958
350	0,963	0,910
334	0,877	0,720
320	0,626	0,310
310	0,370	0,130
300	0,140	0,020
290		
280		
270		
260		
250		

Relative Teildispersionen	
$P_{s,t}$	0,2835
$P_{C,s}$	0,5385
$P_{d,C}$	0,3037
$P_{e,d}$	0,2382
$P_{g,F}$	0,5475
$P_{i,h}$	0,7888
$P'_{s,t}$	0,2810
$P'_{C',s}$	0,5817
$P'_{d,C'}$	0,2531
$P'_{e,d}$	0,2362
$P'_{g,F'}$	0,4860
$P'_{i,h}$	0,7819

Abweichungen rel. Teil- dispersionen $\Delta P$ von der "Normalgeraden"	
$\Delta P_{C,t}$	0,0094
$\Delta P_{C,s}$	0,0041
$\Delta P_{F,e}$	-0,0007
$\Delta P_{g,F}$	-0,0015
$\Delta P_{i,g}$	-0,0048

Konstanten der Dispersionsformel	
$B_1$	1,15687082
$B_2$	0,0642625444
$B_3$	0,872376139
$C_1$	0,00809424251
$C_2$	0,0386051284
$C_3$	104,74773

Sonstige Eigenschaften	
$\alpha_{-30/+70^\circ C} [10^{-6}/K]$	6,5
$\alpha_{+20/+300^\circ C} [10^{-6}/K]$	7,4
$T_g [^\circ C]$	459
$T_{10}^{13,0} [^\circ C]$	453
$T_{10}^{7,6} [^\circ C]$	691
$c_p [J/(g \cdot K)]$	0,770
$\lambda [W/(m \cdot K)]$	1,120
$\rho [g/cm^3]$	2,52
$E [10^3 N/mm^2]$	65
$\mu$	0,190
$K [10^{-6} mm^2/N]$	3,12
$HK_{0,1/20}$	470
<b>HG</b>	4
<b>CR</b>	1
<b>FR</b>	0
<b>SR</b>	1
<b>AR</b>	1
<b>PR</b>	1,2

Konstanten der Formel für $dn/dT$	
$D_0$	$4,86 \cdot 10^{-6}$
$D_1$	$1,72 \cdot 10^{-8}$
$D_2$	$-3,02 \cdot 10^{-11}$
$E_0$	$3,82 \cdot 10^{-7}$
$E_1$	$4,53 \cdot 10^{-10}$
$\lambda_{TK} [\mu m]$	0,26

Farbcode	
$\lambda_{80}/\lambda_5$	33/30
(* = $\lambda_{70}/\lambda_5$ )	

Bemerkungen	
bleihaltig glass type	

Temperaturkoeffizienten der Lichtbrechung						
[ $^\circ C$ ]	$\Delta n_{rel}/\Delta T [10^{-6}/K]$			$\Delta n_{abs}/\Delta T [10^{-6}/K]$		
	1060,0	e	g	1060,0	e	g
-40/ -20	3,3	3,9	4,5	1,3	1,8	2,4
+20/ +40	3,6	4,2	4,9	2,3	2,9	3,6
+60/ +80	3,8	4,5	5,2	2,8	3,4	4,2