

LLF1HTi
548459.294

$n_d = 1,54815$	$v_d = 45,90$	$n_F - n_C = 0,011942$
$n_e = 1,55099$	$v_e = 45,62$	$n_{F'} - n_{C'} = 0,012078$

Brechzahlen		
	λ [nm]	
$n_{2325,4}$	2325,4	1,51863
$n_{1970,1}$	1970,1	1,52354
$n_{1529,6}$	1529,6	1,52886
$n_{1060,0}$	1060,0	1,53473
n_t	1014,0	1,53544
n_s	852,1	1,53848
n_r	706,5	1,54259
n_C	656,3	1,54459
$n_{C'}$	643,8	1,54515
$n_{632,8}$	632,8	1,54568
n_D	589,3	1,54804
n_d	587,6	1,54815
n_e	546,1	1,55099
n_F	486,1	1,55653
$n_{F'}$	480,0	1,55723
n_g	435,8	1,56328
n_h	404,7	1,56904
n_i	365,0	1,57920
$n_{334,1}$	334,1	
$n_{312,6}$	312,6	
$n_{296,7}$	296,7	
$n_{280,4}$	280,4	
$n_{248,3}$	248,3	

Reintransmissionsgrad τ_i		
λ [nm]	τ_i (10mm)	τ_i (25mm)
2500	0,744	0,477
2325	0,804	0,579
1970	0,930	0,833
1530	0,996	0,990
1060	0,999	0,999
700	0,999	0,999
660	0,999	0,998
620	0,999	0,998
580	0,999	0,998
546	0,999	0,998
500	0,999	0,998
460	0,999	0,998
436	0,999	0,997
420	0,999	0,997
405	0,999	0,997
400	0,999	0,997
390	0,998	0,996
380	0,998	0,995
370	0,998	0,994
365	0,997	0,993
350	0,993	0,982
334	0,955	0,892
320	0,721	0,441
310	0,231	0,026
300		
290		
280		
270		
260		
250		

Relative Teildispersionen	
$P_{s,t}$	0,2544
$P_{C,s}$	0,5114
$P_{d,C}$	0,2985
$P_{e,d}$	0,2376
$P_{g,F}$	0,5656
$P_{i,h}$	0,8512
$P'_{s,t}$	0,2515
$P'_{C',s}$	0,5523
$P'_{d,C'}$	0,2485
$P'_{e,d}$	0,2349
$P'_{g,F'}$	0,5014
$P'_{i,h}$	0,8416

Abweichungen rel. Teil- dispersionen ΔP von der "Normalgeraden"	
$\Delta P_{C,t}$	0,0031
$\Delta P_{C,s}$	0,0015
$\Delta P_{F,e}$	-0,0003
$\Delta P_{g,F}$	-0,0010
$\Delta P_{i,g}$	-0,0062

Konstanten der Dispersionsformel	
B_1	1,22510445
B_2	0,125155671
B_3	0,892236751
C_1	0,00870432098
C_2	0,0427325235
C_3	108,049968

Sonstige Eigenschaften	
$\alpha_{-30/+70^\circ\text{C}} [10^{-6}/\text{K}]$	8,1
$\alpha_{+20/+300^\circ\text{C}} [10^{-6}/\text{K}]$	9,2
$T_g [^\circ\text{C}]$	431
$T_{10}^{13,0} [^\circ\text{C}]$	426
$T_{10}^{7,6} [^\circ\text{C}]$	628
$c_p [\text{J}/(\text{g}\cdot\text{K})]$	0,650
$\lambda [\text{W}/(\text{m}\cdot\text{K})]$	0,990
$\rho [\text{g}/\text{cm}^3]$	2,94
$E [10^3 \text{N}/\text{mm}^2]$	60
μ	0,208
$K [10^{-6} \text{mm}^2/\text{N}]$	3,05
$HK_{0,1/20}$	450
HG	
CR	1
FR	0
SR	1
AR	2
PR	1

Konstanten der Formel für dn/dT	
D_0	$2,55 \cdot 10^{-7}$
D_1	$1,41 \cdot 10^{-8}$
D_2	$-3,32 \cdot 10^{-11}$
E_0	$6,74 \cdot 10^{-7}$
E_1	$6,27 \cdot 10^{-10}$
$\lambda_{TK} [\mu\text{m}]$	0,227

Farbcode	
λ_{80}/λ_5	33/31
(* = λ_{70}/λ_5)	

Bemerkungen	
i-Linienglas	

Temperaturkoeffizienten der Lichtbrechung						
	$\Delta n_{rel}/\Delta T [10^{-6}/\text{K}]$			$\Delta n_{abs}/\Delta T [10^{-6}/\text{K}]$		
$[\text{^\circ C}]$	1060,0	e	g	1060,0	e	g
-40/ -20	1,7	2,6	3,5	-0,4	0,5	1,4
+20/ +40	1,8	2,9	3,9	0,5	1,5	2,5
+60/ +80	2,0	3,1	4,2	0,9	2,0	3,1