

# SCHOTT Vitryxx® Bioactive Glass

## For Skin Care

### Product Information


Vitryxx® Bioactive Glass is composed of four oxides that are essential for the human body: namely, silicon oxide, sodium oxide, calcium oxide and phosphor oxide. This inorganic material is made from natural raw ingredients such as sand and soda and purified at more than 1400 °C.

Vitryxx® has the following properties:

- Biocompatible and skin-friendly ingredient for all skin types
- Insensitive to heat or UV-light and temperature extremes
- Builds hydroxyapatite on its surface

### Used in cosmetics, Vitryxx® offers additional benefits:

- Strong anti-oxidative efficacy
- Substantial reduction in skin redness
- Improvement in skin appearance within a short period of time with a visible reduction of wrinkles




SCHOTT Vitryxx®: Visible anti-wrinkle efficacy  
FOITS (Fast Optical in vivo topometry of human skin) measurements


	Vitryxx®   4 µm conc. 1 mg/ml	Blank sample
-UV	13.35 nmol DNPH*/mg protein 33%	40.91 nmol DNPH*/mg protein 100%
+UV	19.60 nmol DNPH*/mg protein 48%	89.02 nmol DNPH*/mg protein 218%
"shows a strong anti-oxidative effect"		Schrader Inst. 2003

*Performed with human keratinocytes \*DNPH Dinitrophenyl-hydrazin | Anti-oxidative efficacy in Protein-Carbonyl-Assay test (R. L. Levine et al, Meth. Enzymol. 186, 464-478, 1990)*


Vitryxx®: Protein-Carbonyl-Assay test readings



Vitryxx®: Redness reduction effect in chemical skin barrier damage study



Redness reduction effect in 24-Hr UV-induced erythema studies



# SCHOTT Vitryxx® Bioactive Glass

For Skin Care

## Formulation Guideline:


Vitryxx® Bioactive Glass is activated by the moisture from water-based products or natural skin. Upon activation Vitryxx® will release mineral ions into the formulation or onto the skin. The system reaches equilibrium after 30-60 minutes.

In general, low loading factors (< 1.0%) will support a stable Water/Oil and Oil/Water formulation. To maintain a stable and compatible formulation at higher concentrations, a predispersion with a high viscous hydrophilic liquid can be used. Carbopol® Aqua SF-1 (alkali-swelling acrylic emulsion polymer), for example, works effectively with Vitryxx®. Fragrances that are compatible with high pH levels should be selected. Raw materials that tolerate high ion content would help in obtaining good hydrous formulations. The possible effect of increased pH in the formulation can be buffered down to pH 5 to 6.

Vitryxx® demonstrated a gelling effect on some formulations (e.g. liquid foundation). With a density of approx. 2.7 g/cm<sup>3</sup> it also tends to settle down in low-density fluids. Pre-dispersing Vitryxx® Bioactive Glass with equal or higher amount of viscous hydrophilic liquid (e.g. glycerine) or preactivation in water can help in obtaining a homogeneous dispersion.

Pre-blending Vitryxx® with Mica improves its dispersibility and enhances the appearance of the formulation. SCHOTT also offers the option of premixed Vitryxx® M, Bioactive Glass with Mica.

Carbopol® is a registered trade mark of Lubrizol.



Electronic Packaging  
**SCHOTT AG**  
Christoph-Dorner-Strasse 29  
84028 Landshut  
Germany  
Phone: +49 (0)871/826-702  
Fax: +49 (0)3641/28889090  
info.glass@schott.com

[www.schott.com/epackaging](http://www.schott.com/epackaging)

**SCHOTT**  
glass made of ideas