

**Band filters**  
**Spectral range**  
**334 nm to 399 nm**

Type	DAD 15 (3 cavities)
$\lambda_m$ -tolerance [% of $\lambda_m$ ]	$\pm 1.5$
Available with $\lambda_m$ in range [nm]	334–399
<b>Spectral values</b>	
Half width HW [nm]	12–18
Maximum spectral transmittance $\tau_{\max}$ within passband	$\geq 0.3$
$Q = \frac{\text{tenth width}}{\text{half width}}$	approx. 1.5
$q = \frac{\text{thousandth width}}{\text{half width}}$	approx. 3.5
Blocking range [nm]	unlimited ( $\lambda_m$ from 334 nm to 360nm) up to 1200 <sup>1)</sup> ( $\lambda_m$ from 361 nm to 399 nm)
Average value $\tau_{SM}$ of spectral transmittance within blocking range	$\leq 10^{-5}$
<b>Other properties</b>	
Humidity resistance of filters with preferred dimensions	MIL-Std-810 C, method 507, proc. 1 : 5 cycles
Operating temperature	up to 70 °C for several hours up to 100 °C for short periods
Temperature dependence of $\lambda_m$ $\Delta\lambda_m/\Delta T$ [nm/°C]	approx. +0.01
Notes	<sup>1)</sup> Unlimited blocking range by additional blocking filters on request. Filter specification can, however, be changed because of this.

Table 5: Specifications of filter type DAD 15

Preferred dimensions [mm]	
External dimensions	Dimensions of utilizable area
$\varnothing 12 +0/-0.3$	$\varnothing \geq 9$
$\varnothing 25 +0/-0.3$	$\varnothing \geq 22$
$\varnothing 50 +0/-0.3$	$\varnothing \geq 47$
Thickness	$\leq 7$
Other dimensions on request	




Fig. 13: Spectral transmittance curve (general curve) of filter type DAD 15